



# Specs: 26.32Specs23

The "DRIZORO SYSTEM" for below ground Waterproofing.

## Products required

- **MAXPLUG or MAXREST**
- **MAXSEAL SUPER**
- **MAXSEAL FLEX**
- **MAXREST PASSIVE**
- **MAXJOINT ELASTIC**

## Method

1. Prepare area to be treated by removing any loose materials ensuring a clean and sound surface.
2. Apply Maxrest Passive to exposed steel to protect against corrosion, if required.
3. Any damage to the surface should be repaired using **MAXPLUG or MAXREST**.
4. **FLOORS:-** Thoroughly wet the entire surface before applying **MAXSEAL SUPER**.
5. **M/S** can be cast, blown, as a "DRY SHAKE" or wet applied by spray in a cross hatch. 2Kg/m<sup>2</sup> total
6. Concrete can be poured after 2 hours
7. When concrete has been levelled and can be walked over, wet surface and spread powder at 2kg/m<sup>2</sup> before trowelling off.
8. **WALLS:- MAXSEAL FLEX** is applied by brush/broom or sprayed. 2 coats at 1.0 kg per coat
9. Leave over night between coats.
10. Dampen surface before applying second coat.
11. When **rendering** over **MAXSEAL FLEX** a slurry coat or "flick coat" should be "flick" applied to the surface to assist with adhesion.
12. **FLOOR/WALL JOINTS:- Apply MAXSEALFLEX** at the rate of 2 KG/m<sup>2</sup> to the area where walls are to be poured or the area where floors are to be poured to provide a waterproof seal. Allow 6 hours before pour.
13. Leave for 4-5 days to cure before finishing surface. **DRIZORO** products are suitable for use with many popular finishing products including, paints, decorative renders.

Please contact our office if you require further information. *This information is based on information from the manufacturer and from our own experience. The information contained in this specification should be used in conjunction with the appropriate technical data bulletins and material safety data sheets available from our office or website.*

