



Specs: 26.3165Specs23

Repair and Waterproofing, damaged Lintels

Products required

- **MAXGROUT/MAXREST**
- **MAXSEALFLEX**
- **MAXREST PASSIVE**

Method:

1. Prepare area to be treated by removing any loose materials ensuring a clean and sound surface.
2. Any exposed metal surfaces- wire brush to remove loose material.
3. Apply Maxrest Passive to all metal surfaces to prevent future oxidization.
4. Apply Maxgrout/Maxrest to bring area back to previous.
5. If rain is expected within 5 hrs. of application, do not apply.
6. Allow to cure overnight wet area and apply Maxsealflex at the rate of 1kg/m². Allow to cure 14 hours and apply second coat of Maxsealflex.

Lintels with minor cracking up to 3mm

1. Wet surface and apply Maxsealflex to exposed surface at the rate of 1kg/m². Allow to cure 14 hours and apply second coat of Maxsealflex.

General:

To ensure waterproofing protection apply Maxsealflex to all remaining Lintels

1. Ensuring that the surfaces are very wet between each application, apply two coats of **MAXSEALFLEX** to all remaining Lintel surface areas as in 6. above.
2. Allow 14 hours minimum and 3 days maximum between coats.
3. Allow 14 days before applying any paint, stone, tiles or cement
4. If any efflorescence is noted prior to the application, please contact this office for further advice regarding efflorescence removal.

Note – This information is based on information from the manufacturer and from our own experience. The information should be used in conjunction with the appropriate technical data bulletins and material safety data sheets available from our office or website